

TEST REPORT

No.: TJIN1501000202ML

Date: Jun. 15, 2024

Page: 1 of 2

CUSTOMER NAME: TIANJIN HUAYOU SCAFFOLDING CO.,LTD.

ADDRESS: ROOM331,HUAYING BUILDING, AIRPORT ECONOMIC ZONE,

TIANJIN CITY, CHINA

The following sample(s) was/ were submitted and identified on behalf of the client as:

Sample Name : Galvanized Steel Pipe

Quantity : 1

Product Specification : 48.3mm * 3.2mm

Material and Mark : Q235

Date of Receipt : Jun 08, 2024
Testing Start Date : Jun 08, 2024
Testing End Date : Jun 15, 2024

Test result(s) : For further details, please refer to the following page(s)

Signed for

SGS-CSTC Standards Technical Services(Tianjin) Co., Ltd

Kevin Zhou

Authorized signatory



This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is set of the terms of the



TEST REPORT

No.: TJIN1501000202ML

Date: Jun. 15, 2024

Page: 2 of 2

1.Test item: Chemical Composition Analysis

Result:

Element	С	Si	Mn	Р	S	N*	Conclusion
Req.,%	≤0.20	≤0.30		≤0.050	≤0.050	≤0.009	
Result ,%	0.14	0.14	0.37	0.032	0.014	0.0072	Pass

Note: The results comply with the requirement of BS 1139-1.1:1990.

2.Test item: Tensile Test

Test Method: BS EN 6892-1:2009

	Specimen	Tensile strength	Yield strength	Elongation after						
Test item	type	(R _m)	(R _{eH})	fracture(A)	Conclusion					
		(MPa)	(MPa)	$L_o = 5.65 \sqrt{So}$ (%)						
		≥340								
Req.		<480	≥235	≥24						
1#	Tubular Strip		390		Pass					
	specimen	442		28.0						

Note: The results comply with the requirement of BS 1139-1.1:1990. ****** End of report******



This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is devised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized atteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@ass.com

No. 555, Central Avenue, TAEA, China. 300345 中国・天津・空港经济区中心大道555号 邮编: 300345 t (86-22) 59803788 t (86-22) 59803788

f (86-22) 59803777

e sgs.china@sgs.com

^{*}The above test was carried out by an external laboratory assessed as competent.