



National Test Center of
Polymer & Building Materials



中国认可
检测
TESTING
CNAS L1049

Address: No. 14, Beisanhuandonglu, Chaoyang district, Beijing, China Post Code : 100013
Tel: +86(0)1064208747, +86(0)1064200694, +86(0)1064224642, +86(0)1059202479
Fax: +86(0)1059202784, +86(0)1084290301 Web site : www.plastic-test.net

TESTING RESULTS

No.2019(C) 03038

No.	Test Items		Requirements	Results	Test methods
1	Shore hardness (D)		≥ 58	66	GB/T 2411-2008
2	Charpy un-notched impact strength, kJ/m^2		≥ 30	68.2(C)	GB/T 1043.1-2008
3	Flexural strength, MPa		≥ 30	42.7	GB/T 9341-2008
4	Flexural modulus of elasticity, MPa		≥ 3000	3.17×10^3	GB/T 9341-2008
5	Heat reversion, %	transverse	± 0.2	+0.14	JG/T 418-2013 7.2.7
		longitudinal	± 0.2	-0.18	JG/T 418-2013 7.2.7
6	Water absorption, %		≤ 0.5	0.45	GB/T 1034-2008
7	Vicat softening temperature (B_{50}), $^{\circ}\text{C}$		≥ 80	80.3	GB/T 1633-2000

(THE PART BELOW IS BLANK)



Test: 杨勇 郭书超