

TEST REPORT

No.: TJIN2104005656CM

Date: Apr 26, 2023

Page: 1 of 3

TIANJIN HUAYOU SCAFFOLDING CO., LTD **CUSTOMER NAME:**

ADDRESS: ROOM331, HUAYING BUILDING, AIRPORT ECONOMIC ZONE,

TIANJIN CITY, CHINA

Sample Name Metal plank

Product Specification 210*45*3000mm

Manufacturer Tianjin Huayou Scaffolding Co., Ltd

Material and Mark Q195

Above information and sample(s) was/were submitted and confirmed by the client. SGS, however, assumes no responsibility to verify the accuracy, adequacy and completeness of the sample information provided by client.

Date of Receipt Apr 21, 2023 **Testing Start Date** Apr 21, 2023 **Testing End Date** : Apr 26, 2023

Test result(s) For further details, please refer to the following page(s)

(Unless otherwise stated the results shown in this test report refer only to

the sample(s) tested)

Signed for

SGS-CSTC Standards Technical Services(Tianjin) Co., Ltd

Duke Gai

Authorized signatory





TEST REPORT

No.: TJIN2104005656CM

Date: Apr 26, 2023

Page: 2 of 3

Test Item: Deflection and Bending Test

Test Method: With reference to SS 280: Part1:2006 Annex F.1 and client's requirement

Sample Description:

Metal plank 3000mm × 210mm × 45mm (Length × Width × Height)

Test Condition:

Specimen: Metal plank, 2pcs

Test span: 1800mm

Test Result:

1 out recount.					
Sample	e ID	Deflection at the center of the span	Maximum load (kN)		Requirement (Table 3)
	under load 0.82kN (mm)	Individual	Average		
1#		1.97	3.86	3.81	Deflection≤10mm Individual≥2.06 kN Average≥2.27 kN
2#		1.91	3.76	3.01	

Note:

1. The vertical deflection of any individual sample shall not exceed 10mm, the load is (0.00392 x width of catwalk in mm) kN

2.Bending strength:

Average: (width of treadboard in mm x 0.0108) kN minimum Individual: (width of treadboard in mm x 0.0098) kN minimum





TEST REPORT

No.: TJIN2104005656CM

Date: Apr 26, 2023

Page: 3 of 3

Original Sample Photo:



Note: The test report shall only be used for clients' scientific research, teaching, internal quality control, product research and development, etc... and just for internal reference.

****** End of report******

